

Last Patch Limestone Mixing Instructions

Safety


When using any of our products, Bonstone recommends the use of appropriate safety apparel which includes gloves, masks, and safety glasses. Be sure to review safety and technical data sheets.

Mixing Instructions


Last Patch™ Limestone is mixed 7 parts (by weight) of "A" side (thick sand-like mortar) to 1 part "B" side (clear watery). There are two different methods for achieving this mix ratio:

Method #1

- 1) Take one cup and fill it until it reaches the 1 oz mark with part "A". (This gives you 49 grams of "A")
- 2) Take another cup and fill it with part "B" until it reaches the 1 tsp mark. (This gives you 7 grams of "B")
- 3) In a separate container combine both "A" and "B" from the above containers and thoroughly mix the material and immediately use.



Fill Part A to 1oz




Fill Part B to 1tsp

Method #2

- 1) Take the cup provided and fill to top with part "A" four times while emptying each cup into a separate mix container. (This gives you 196 grams of part "A")
- 2) Empty an entire tube of the "B" side into the container.
- 3) Thoroughly mix the material that was just measured out and immediately apply to repair area.

* Note: Add more part A if needed to get a "mortar-like" consistency



Fill Part A to top



Whole tube

Mixing Tips

- Product is a 7:1 ratio by Weight
- If desired, you can add up to 10% of your own stone dust.
- Wear latex gloves to form the material around corners.
- Use powdered tints to adjust for variations in stone color.
- Apply the material as flush as possible on the surface of the stone before dry grinding, thus reducing grinding time.
- Mix to a mortar consistency.